Functionalization of Carbon Nanotubes Using A Silane Coupling Agent

Peng Cheng MA¹, Jang-Kyo KIM^{1*} and Ben Zhong TANG²

Addresses and affiliations for the authors:

Peng Cheng MA

Tel.: +852 2358 8657; Fax: +852 2358 1543. E-mail: mapc@ust.hk.

Address: Department of Mechanical Engineering, the Hong Kong University of Science & Technology,
Clear Water Bay, Kowloon, Hong Kong, China

Jang-Kyo KIM (Corresponding Author)

Tel.: +852 2358 7207; Fax: +852 2358 1543. E-mail: mejkkim@ust.hk.

Address: Department of Mechanical Engineering, the Hong Kong University of Science & Technology,
Clear Water Bay, Kowloon, Hong Kong, China

Ben Zhong TANG

Tel.: +852 2358 7375; Fax: +852 2358 1594. E-mail: tangbenz@ust.hk.

Address: Department of Chemistry, the Hong Kong University of Science & Technology, Clear Water
Bay, Kowloon, Hong Kong, China

Functionalization of Carbon Nanotubes Using A Silane Coupling Agent

Peng Cheng MA¹, Jang-Kyo KIM^{1*} and Ben Zhong TANG²

¹Department of Mechanical Engineering and ²Department of Chemistry

The Hong Kong University of Science & Technology, Clear Water Bay, Kowloon, Hong Kong, China

Abstract

A new method is developed to chemically functionalize multi-walled carbon nanotubes (MWCNTs) based on silanization reaction for use as the reinforcement for polymer matrix composites. To oxidize and create active moieties on the MWCNTs, the samples were exposed to UV light within the ozone chamber, followed by silanization using 3-glycidoxypyltrimethoxy silane after the oxidized MWCNTs were reduced by lithium aluminum hydride. FT-IR, TEM and XPS were employed to characterize the changes in carbon nanotubes surface morphology, chemistry and physical conditions at different processing stages. The results indicate improved dispersion and attachment of silane molecules on the surface of the MWCNTs.

Keywords:

Carbon nanotubes; Surface treatment; Functional groups; Surface properties

1. Introduction

With unique structural and transport properties, such as excellent strength, modulus, electrical and thermal conductivities along with low density, carbon nanotubes (CNTs) have attracted much interest in the field of CNT/polymer nanocomposites [1-3]. These composites hold the promise of delivering exceptional mechanical properties and multi-functional characteristics. However, if these materials

* Corresponding author. Tel.: +852 2358 7207; Fax: +852 2358 1543. E-mail: mejkkim@ust.hk.

are to be utilized as effective reinforcements in polymer composites, proper dispersion and good interfacial bonding between the CNTs and the polymer matrix have to be guaranteed [4]. Therefore, many different surface treatment and functionalization techniques [5] have been devised for improving the dispersion and interfacial adhesion of CNTs with polymer resins. Among these methods, high concentration acids treatment has shown promising results to provide functional groups (carboxyl groups) onto the CNTs surface. This method, however, not only creates defects on the CNT sidewalls, but also decreases the aspect ratio of CNTs because the strong acids cut the CNTs into short pieces during the oxidative process [6, 7]. The defects severely degrade the mechanical properties of CNTs. Ozone treatment of the CNTs has been developed as an alternative, milder method [8, 9] where the surface of the nanotubes is decorated with active moieties, thus substantially broadening the chemical reactivity of the CNTs. These ameliorating effects have been further improved by incorporating with UV light [10].

Polysiloxane of various kinds has been widely used as coupling agents between glass substrates and polymeric resins [11]. The coupling process can be accomplished via the chemical reaction between the trialkoxy groups of silane molecules and the hydroxyl groups on the glass substrates, whereas other functional groups of silane molecules, which are generally ethylene, amine, epoxy, thiohydroxy, etc, can be remained. Recently, this process has been applied to functionalize the CNTs surface [12-14].

This paper is part of a larger project on the development of surface treatment techniques for carbon nanotubes as the reinforcement of polymer matrix nanocomposites. A new method is presented for the chemical functionalization of multi-walled carbon nanotubes (MWCNTs) through the combined process of UV/O₃ treatment and silanization reaction. The silane molecules containing epoxy ended-groups are covalently bonded on the surface of the MWCNTs, which in turn modifies the surface characteristics of the MWCNTs and improves the compatibility of MWCNTs with epoxy.

2. Experimental

2.1 Materials

MWCNTs used in this study are basically the same as those employed in our previous work [10], which were prepared by a chemical vapor deposition method (supplied by Iljin Nanotech Ltd., Korea). The diameter and length ranged between 10–20 nm and 10–50 μm , respectively, according to the supplier's specification. 3-Glycidoxypyriltrimethoxy silane (GPTMS) with purity of 98 % (supplied by Aldrich) was used as the silane functionalization agent. The following reagents and solvents were used without further purification: toluene (99.5%, BDH), ethanol (99.9%, Merck), methanol (>99.5%, Fisher), acetone (99.5%, General Chemical), and lithium aluminum hydride (powder, 95%, Aldrich).

2.2 Treatment of MWCNTs

2.2.1 Pretreatment of MWCNTs

A two-step pretreatment of ball milling and ultrasonication was established after an extensive trial and error to disentangle and disperse the MWCNTs before UV/O₃ treatment. Typically, 250 mg of MWCNTs was put into a stainless steel ball milling container with 450 pieces of ZrO₂ milling beads (150 pieces of beads with diameter of 5.5, 3.0 and 2.0 mm, respectively). The rolling speed was fixed at 250 rpm and the milling was continued for 2 h. Then 50 mg MWCNTs were transferred into a beaker containing 60 ml of toluene, and ultrasonically treated using a Digital Sonifier (Branson Ultrasonics Corporation, USA) for 1 h. After the treatment, the solution was filtered through a nylon filter with pore size of 1.0 μm , which was then dried in a vacuum oven at 80°C for 4 h.

2.2.2 Oxidation of MWCNTs

The aim of oxidation treatment was to create active sites and moieties on the surface of nanotubes.

The filtered MWCNTs were dried at 80°C for 4h, which were then subjected to UV/O₃ treatment

in a chamber (Jelight 144AX-220 UV/Ozone Cleaning System) for 2 h. The cleaner contained a low-pressure mercury vapor grid lamp that could release ultraviolet radiation of $28\text{W}/\text{cm}^2$. The wavelength of the ultraviolet light was 253.7 nm, and the distance between the UV lamp and the sample stage was fixed at 20mm.

2.2.3 Reduction of MWCNTs

The reduction of the oxidized MWCNTs was realized using lithium aluminum hydride (LiAlH_4). Typically, 20.0 mg of oxidized MWCNTs was dispersed in toluene by ultrasonication (in a water bath) for 30 min, and then 5.0 mg of LiAlH_4 was added gently. The solution was stirred for 1 h at room temperature, followed by adding 2.0 ml of 2.0 N hydrochloric acid into the solution in order to remove the lithium and aluminum. The reduced MWCNTs were obtained by filtration of the solution and washing with toluene, absolute ethanol and acetone, and then drying in a vacuum oven at 80°C overnight.

2.2.4 Silanization of MWCNTs

20.0 mg of reduced MWCNTs was added into a three-neck flask with 50.0 ml toluene and dispersed through ultrasonication (in a water bath) for 30 min. Then 7.5 ml of 1.0 wt % toluene solution of GPTMS was added and stirred for 6 h at $60\text{--}65^\circ\text{C}$ for silanization. After the reaction, 30 ml of methanol was added to dilute the unreacted GPTMS molecules. The product was obtained by filtration and washing with methanol, water and acetone sequentially. The silane treated MWCNTs were dried in a vacuum oven at 80°C for 12 h.

2.3 Characterization of MWCNT Surface

Fourier transform infrared (FTIR) spectrometry, X-ray photoelectron spectroscopy (XPS) and field emission analytical transmission electron microscope (TEM) were used to characterize the changes in chemical structure and surface morphology of the MWCNTs after each surface

treatment step. For the FTIR (Perkin Elmer Spectrum One, USA), the MWCNTs were pressed into a pellet with potassium bromide (KBr) and scanned from 500 cm^{-1} to 4000 cm^{-1} at a resolution of 4 cm^{-1} . TEM images were taken on a JEOL 2010F (JEOL Ltd., Japan) with an energy dispersion X-ray (EDX) analyzer. In the XPS analysis (Surface analysis PHI5600, Physical Electronics, Inc.), a monochromatic Al K α X-ray was used at 14 kV. The XPS curve fitting of C1s and Si 2p was accomplished by MultiPak V6.0 A (Physical Electronics, Inc.).

3. Results and discussion

3.1 Surface Functionalities of MWCNTs

Figure 1 shows the FTIR results of the MWCNTs obtained at different processing steps. For the pristine MWCNTs (Fig. 1A), the bands at 3419 and 1058 cm^{-1} are attributed to the presence of hydroxyl groups (-OH) on the surface of the MWCNTs, which are believed to result from either ambient atmospheric moisture bound to the MWCNTs or oxidation during purification of the raw material [15]. Another band at 1626 cm^{-1} is assigned to the C=O stretching of quinone groups on the surface of MWCNTs.

For the oxidized MWCNTs (Fig. 1B), two new bands appeared at 1715 and 1160 cm^{-1} , which are attributed to the C=O and C-O stretching vibrations of the carboxylic groups (-COOH), respectively. The increase in the relative intensities of the bands at 1068 and 3420 cm^{-1} (I_{1068}/I_{3420}) suggests that there are more -OH groups on the MWCNT surface after the oxidation. All these observations confirm that the surface of the MWCNTs has been functionalized or activated by the UV/O₃ treatment.

The FT-IR spectrum of the reduced MWCNTs (Fig. 1C) shows the reduction of the -COOH groups to -OH groups, as verified by the disappearance of the band at 1715 cm^{-1} and the appearance of a band at 1384 cm^{-1} , which is assignable to the bending vibration of the -OH group.

In the silane-functionalized MWCNTs (Fig. 1D), the band at 3410 cm^{-1} became broader and weaker, and the band at 1384 cm^{-1} almost disappeared. On the other hand, two new bands at 2914 and 2848 cm^{-1} associated with the stretching of the methylene groups from the GPTMS molecules appeared. The weak signal at 793 cm^{-1} confirms the presence of the epoxy group on the GPTMS-modified MWCNTs. Although there is a possibility of reactions between --OH and epoxy group, this reaction can only be accomplished in the presence of catalysts, such as tertiary amine [16]. In our experiment, toluene was used as the reaction media, and the temperature was controlled at $60\text{--}65^\circ\text{C}$. Therefore, the chance for reactions between --OH and epoxy was very small. This conclusion along with the FT-IR spectral data confirm that the --OH groups of the MWCNTs could react only with the --OCH_3 groups of the GPTMS molecules.

Fig. 1. FTIR spectra of the MWCNTs (A: Pristine, B: UV/ O_3 -treated, C: Reduced, D: Silanized)

3.2 Dispersion and Surface Morphology of the MWCNTs

In order to compare the suspension stability of the MWCNTs obtained at different processing steps, ethanol solutions with a MWCNTs concentration of 0.5 mg/ml were prepared. Figure 2 shows the results of the suspending states of the MWCNTs samples after 5 minutes of dispersion via sonication. Comparison of these photographs indicates that the suspension stability of the pristine MWCNTs (Fig. 2A) was poor: they easily sedimented in ethanol due to the agglomeration and poor hydrogen-bonding ability. The pretreated MWCNTs showed better stability than the pristine ones only in the short term (Fig. 2B, left panel), and phase separation occurred after 24 h (Fig. 2B, right panel). For the chemically modified MWCNTs (Fig. 2C–E), the functional groups on the surface of MWCNTs enhanced their hydrogen-bonding abilities. This led to the improved suspension stability compared with the pristine and pretreated ones, through the conversion of the MWCNT surface from a hydrophobic to a hydrophilic state. The MWCNTs functionalized by GPTMS (Fig. 2E, right panel) presented the best stability both in the short and long terms, due to the functionalization effect on their surface.

Fig. 2. Suspension stability of the MWCNTs (A: Pristine, B: Pretreated, C: UV/O₃-treated, D: Reduced, E: Silanized)

Figure 3 shows the typical TEM images of the MWCNTs at different processing steps. The pristine

MWCNTs were severely agglomerated (Fig. 3A). After the pretreatment using ball milling and ultrasonic irradiation (Fig. 3B), the agglomeration was significantly reduced. The chemically modified MWCNTs (Fig. 3C–E) showed much improved dispersion with few agglomerates. The individual MWCNTs were detached loosely without significant changes in their lengths. These results are in agreement with the observations described above in reference to Fig. 2 that the chemically modified MWCNTs exhibited improved suspension stability in ethanol.

Fig. 3. Dispersion of MWCNTs (A: Pristine, B: Pretreated, C: UV/O₃-treated, D: Reduced, E: Silanized).

The surface morphologies of the MWCNTs at different processing steps are shown in Figure 4. As can be seen from Fig. 4A, the end tips of the pristine MWCNT were closed. After the pretreatment through ball milling and ultrasonication (Fig. 4B), however, the end tips of many MWCNTs were open, a reflection of broken C-C bonds along the graphene layers of the co-axial tubes. This observation is in agreement with the previous report [17].

Fig. 4. Surface morphology of MWCNTs (A: Pristine, B: Pretreated, C: UV/O₃-treated, D: Reduced, E: Silanized).

The sound, layered structure of the pretreated and chemically modified MWCNTs (Fig. 4B–D) indicates that there was little damage to the MWCNTs surface. Some amorphous materials were attached to the end tips of the silane-treated MWCNTs (spot A in Fig. 4E). The detection of silicon by the EDX (Fig. 5A) confirms that these amorphous materials were derived from the silane molecules. The fact that no silicon was detected by the EDX (Fig. 5B) in the inner part of the MWCNTs (spot B in Fig. 4E) verifies that only the surface layer of the MWCNTs has been activated by our method. No GPTMS molecules have penetrated into the tubes during the silanization process.

Fig. 5. EDX Spectrum of the silane-treated MWCNTs

We also investigate the possibility of the damage to the MWCNT surface which was introduced by the silanization reactions. Figure 6 shows the surface morphology of the silane-treated MWCNTs after it was kept at 400°C in nitrogen gas for 1 h. This micrograph suggests that the silane molecules on the MWCNT surface can be removed (spots A and B in Fig. 6). The layered structure of the MWCNTs remained largely intact, and there was no obvious damage to the MWCNTs during the silanization process.

Fig. 6. Surface morphology of the MWCNTs after decomposition of silane molecules.

3.3 XPS Results

Fig. 7. C1s XPS spectrum of MWCNTs (A: Pristine, B: UV/O₃-treated, C: Reduced, D: Silanized)

Figure 7 presents C1s XPS spectra of the MWCNTs. The C 1s peak of the pristine MWCNTs (Fig. 7A) can be deconvoluted into five fitting curves [13, 18] with peaks at 284.5, 285.2, 286.1, 287.4 and 289.4 eV. The last one at 290.7 eV corresponds to a shakeup feature of the aromatic structure present in the MWCNTs [*]. The respective percentages and elemental compositions of the MWCNTs are summarized in Table 1 (excluding the peak at 290.7 eV) and Table 2.

After the UV/ O₃ treatment (Fig. 7B), the components at ~286.2 and ~289.2 eV are attributed to the CO and COO groups, representing 9.09% and 8.67% of the carbon signal (Table 1), which are much higher than those of the pristine MWCNTs. The atomic percentage of the oxygen in the sample also increased significantly from 1.35 % (pristine) to 8.74% (Table 2), indicating that the UV/O₃ process effectively generated more functional groups on the MWCNT surface.

* <http://srdata.nist.gov/xps/index.htm>, NIST standard reference database 20, accessed in March 2006

The MWCNTs after reduction by LiAlH₄ exhibited a different spectrum with the C 1s peak (Fig. 7C). The increase in the relative intensity at ~286.2 eV along with the virtual disappearance of the peaks at ~287.4 eV (C=O) and ~289.2 eV (COO) suggest the conversion of these groups into the alcohol groups (Table 1). This conversion process can be useful in anchoring the GPTMS molecules with the MWCNTs through the reaction between the hydroxyl groups and the methoxyl groups of silane. A small increase of Al arose from the LiAlH₄ that was not completely eliminated by the washing steps.

The GPTMS-functionalized MWCNTs (Fig. 7D) showed a much similar spectrum to that of the reduced ones. However, a new contribution attributed to the Si-C appeared at 282.8 eV along with an element composition of silicon standing at 1.68%. These observations further confirm the presence of silane on the MWCNTs after the reactions.

Table 1 Summary of the relative percentage of the carbon and assignation

Binding Energy (eV)	282.8	284.5	285.1-285.3	286.0-286.5	287.6-287.8	289.0-289.4
and Assignation	Si-C	C _g sp ²	C _d sp ³	C-O	-C=O	CO-O
Pristine	/	73.41	13.28	5.42	4.01	3.88
UV/O ₃ -treated	/	64.35	13.91	9.09	3.98	8.67
Reduced	/	62.37	20.52	12.70	2.56	1.85
Silanized	3.97	60.83	23.88	12.85	0.77	1.67

Table 2 Summary of the element composition of the MWCNTs

Element (Atom %)	C	O	Al	S	Fe	Si
Pristine	98.34	1.35	0.21	0.04	0.06	/
UV/O ₃ -treated	90.93	8.74	0.26	/	0.07	/
Reduced	90.64	8.90	0.40	/	0.06	/

Silanized 88.51 9.38 0.38 / 0.05 1.68

Fig. 8. Si 2p XPS spectrum of silane-treated MWCNTs

Figure 8 shows deconvoluted Si 2p signal of the silane-treated MWCNTs. The two peaks at different binding energies indicate that there were two chemical states of Si. These can be explained by the reaction illustrated in Figure 9: the first one at a binding energy of 101.6 eV represents the bond of silicon with oxygen originating from the MWCNTs (Si–O–CNT, reaction A in Fig. 9) [12]; the second one at 103.3 eV is attributed to the siloxane (–Si–O–Si–) resulting from the partial hydrolysis of the GPTMS molecules (reaction B in Fig. 9) during the silanization reaction [12]. These results are in good agreement with the reaction mechanisms of silane, including hydrolysis of –OCH₃, condensation to oligomers, hydrogen bond between oligomer and OH groups on the substrate, and the formation of the covalent linkage between silane and the substrate [11]. The relatively high percentage of the first contribution (80.03% vs 19.97%) confirms that the main reaction occurred between the GPTMS molecule and the surface of the reduced MWCNTs.

Fig. 9. Schematics of the reactions taking place between the reduced MWCNTs and the silane

4. Summary

In this work, we developed a method for the chemical functionalization of the MWCNTs through a combined process of UV/O₃ treatment and silanization reaction. The hydrophobic surface of the MWCNTs was converted to hydrophilic through UV/O₃ and silane treatments. The results indicate good dispersion of MWCNTs in ethanol and attachment of silane molecules containing epoxy end-groups on the MWCNT surface via the reaction of the –OH groups of the MWCNTs and the –OCH₃ groups of the silane molecules. This in turn would contribute to enhancing the MWCNT's compatibility with polymer matrix, which will be the subject of forthcoming publications.

Acknowledgements

This project is supported by the Research Grant Council of Hong Kong SAR (Project number 614505). Technical assistance from the Materials Characterization and Preparation Facilities (MCPF) of HKUST is also appreciated.

References

- [1]. Thostenson ET, Ren ZF, Chou TW. Advances in the science and technology of carbon nanotube and their composites: a review. *Compos Sci Technol* 2001; 61: 1899–912
- [2]. Coleman JN, Khan U, Gun'ko YK. Mechanical reinforcement of polymers using carbon nanotubes. *Adv Mater* 2006; 18: 689–706
- [3]. Tang BZ, Xu HY. Preparation, alignment, and optical properties of soluble poly(phenylacetylene) wrapped carbon nanotubes. *Macromolecules* 1999; 32: 2569-76
- [4]. Fiedler B, Gojny FH, Wichmann MHG, Nolte MCM, Schulte K. Fundamental aspects of nano-reinforced composites, *Compos Sci Technol* (In press)

- [5]. Tasis D, Tagmatarchis N, Bianco A, Prato M, Chemistry of Carbon Nanotubes. *Chem Rev* 2006; 106: 1105-36
- [6]. Shen K, Xu H, Jiang Y, Pietraß T. The role of carbon nanotube structure in purification and hydrogen adsorption. *Carbon* 2004; 42:2315–22
- [7]. Monthieux M, Smith BW, Burtiaux B, Claye A, Fischer JE, Luzzi DE. Sensitivity of single-wall carbon nanotubes to chemical processing: an electron microscopy investigation. *Carbon* 2001; 39: 1251-72
- [8]. Lu X, Zhang L, Xu X, Wang N, Zhang Q. Can the sidewalls of single-wall carbon nanotubes be ozonized? *J Phys Chem B* 2002; 106: 2136-39
- [9]. Mawhinney DB, Naumenko V, Kuznetsova A, Yates JT, Liu J, Smalley RE. Infrared spectral evidence for the etching of carbon nanotubes: ozone oxidation at 298 K. *J Am Chem Soc* 2000; 122:2383-84
- [10]. Sham ML, Kim JK. Surface functionalities of multi-wall carbon nanotubes after UV/Ozone and TETA treatments. *Carbon* 2006; 44: 768–77
- [11]. Plueddemann EP. Silane coupling agent. New York: Plenum. 1991: 115-151
- [12]. Velasco-Santos C, Martinez-Hernandez AL, Lozada-Cassou M, Alvarez-Castillo A, Castano VM. Chemical functionalization of carbon nanotubes through an organosilane. *Nanotechnology* 2002; 13: 495–8
- [13]. Vast L, Philippin G, Destree A, Moreau N, Fonseca A, Nagy JB, et al. Chemical functionalization by a fluorinated trichlorosilane of multi-walled carbon nanotubes. *Nanotechnology* 2004; 15: 781–5
- [14]. Deng YH, Deng CH, Yang D, Wang, Fu SK, Zhang XM. Preparation, characterization and application of magnetic silica nanoparticle functionalized multi-walled carbon nanotubes. *Chem Commun* 2005; 44: 5548–50

- [15]. Ramanathan T, Fisher FT, Ruoff RS, Brinson LC. Amino-functionalized carbon nanotubes for binding to polymers and biological systems. *Chem Mater* 2005; 17: 1290-95
- [16]. Sun JM. *Application principle and theory of epoxy resins*. Beijing: China machine press. 2002: 18-22
- [17]. Pierard N, Fonseca A, Konya Z, Willems I, Tendeloo GV, Nagy JB. Production of short carbon nanotubes with open tips by ball milling. *Chem Phys Lett* 2001; 335: 1-8
- [18]. Ago H, Kugler T, Cacialli F, Salaneck WR, Shaffer MSP, Windle AH, Friend RH. Work functions and surface functional groups of multiwall carbon nanotubes. *J Phys Chem B* 1999; 103: 8116-21.

List of Captions for figures and Tables.

Figure 1 FTIR spectra of the MWCNTs (A: Pristine, B: UV/O₃-treated, C: Reduced, D: Silanized)

Figure 2 Suspension stability of the MWCNTs (A: Pristine, B: Pretreated, C: UV/O₃-treated, D: Reduced, E: Silanized)

Figure 3 Dispersion of MWCNTs (A: Pristine, B: Pretreated, C: UV/O₃-treated, D: Reduced, E: Silanized).

Figure 4 Surface morphology of MWCNTs (A: Pristine, B: Pretreated, C: UV/O₃-treated, D: Reduced, E: Silanized).

Figure 5 EDX Spectrum of the silane-treated MWCNTs

Figure 6 Surface morphology of the MWCNTs after decomposition of silane molecules.

Figure 7 C1s XPS spectrum of MWCNTs (A: Pristine, B: UV/O₃-treated, C: Reduced, D: Silanized)

Figure 8 Si 2p XPS spectrum of silane-treated MWCNTs

Figure 9 Schematics of the reactions taking place between the reduced MWCNTs and the silane

Table 1 Summary of the relative percentage of the carbon and assignation

Table 2 Summary of the element composition of the MWCNTs